

Clean Version of Claim Amendments

20. Process according to claim 17, wherein the composition is dissolved in an appropriate solvent system.

21. Process according to claim 17, wherein the composition is applied to provide a coating having dry weight in the range from 1.5 g/m² to 3.0 g/m².

22. Process according to claim 17, wherein the composition is applied to provide a coating on a textured and anodized aluminum substrate or on a polyester substrate.
